

### Technical Data Sheet

Material Designation

Grade F

Material Properties  
Summary

☒ *Binderless*

☐ *Organic Binder*

☐ *Double Laminated*

☐ *Acrylic Binder*

☐ *Laminated*

☐ *Hydrophobic*

This is an ultra high efficiency particulate air filter material especially suited to applications requiring a very high degree of efficiency. The absence of organic binder and fungicide makes this grade eminently suitable for chromatography and analytical filtration.

Binderless media

#### Micron rating

0.7

$\mu m$

#### Basis Weight

45

*lbs/3,000 ft<sup>2</sup>*

*TAPPI Method T410*

#### Caliper Thickness

0.016

*inches - 4 psi*

*TAPPI Method T411*

#### Mean Pore Size

2.8

$\mu m$

#### DOP Smoke Penetration

0.001

*% at 0.3  $\mu m$  @  
10.5 ft/minute*

*ASTM Method D-2986*

#### Air Flow Resistance

51

*mm H<sub>2</sub>O @  
10.5 ft/minute*

*ASTM Method D-2986*

#### Tensile Strength MD

3.0

*lbs / inches*

*TAPPI Method T494*

#### Tensile Strength CD

2.5

*lbs / inches*

*TAPPI Method T494*

#### Dry Elongation MD

2.5

%

*TAPPI Method T494*

#### Dry Elongation CD

2.5

%

*TAPPI Method T494*

#### Frazier Permeability

-

*ft<sup>3</sup> / min / ft<sup>2</sup> @  
0.5in H<sub>2</sub>O W.G.*

*ASTM Method F778-82*

#### Gurley Stiffness

-

*mg*

*TAPPI Method T543*

#### Water Repellency

-

*Inches H<sub>2</sub>O*

#### Ignition Loss

Binderless

*% Loss*

#### Comments:

*Widely used in airborne particulate monitoring applications. Material demonstrates a 99.999% efficiency.*

*Actual filtration performance, i.e. efficiency and dust holding capacity, will vary depending upon filter design parameters and the normal variation of the media properties consistent with the specification range. We continuously strive to define our products and hence the specifications are subject to change.*