


### Technical Data Sheet

#### Description

NOVA-TECH™ cleanroom wipes are made from a hydroentangled nonwoven material composed of 45% polyester and 55% cellulose. These wipes are manufactured in a cleanroom environment and cleanroom packaged.

- Wiping and cleaning all aspects of cleanroom
- Controlling spills
- Removal of solutions such as disinfectants, adhesives, residues, etc.



#### Performance Characteristics:

Test	Value
<b>Basis Weight</b> (g/m <sup>2</sup> )	68 gsm
<b>Thickness</b>	0.30 mm
<b>Absorbency Rate &amp; Capacity</b>	
Absorbency Capacity (IEST-RP-CC004.3, Sec 8.1)	288 mL / m <sup>2</sup>
Absorbency Rate (IEST-RP-CC004.3, Sec 8.2)	0.8 sec
<b>Non-volatile Residue, NVR</b> (IEST-RP-CC004.3, Sec 7.1.2)	
Non-volatile Residue (NVR) in DI water extractant (IEST-RP-CC004.3, Sec 7.1.2)	0.091 mg/g
Non-volatile Residue (NVR) in IPA extractant (IEST-RP-CC004.3, Sec 7.1.2)	0.431 mg/g
<b>Releasable Particles</b>	
LPC ≥ 0.5 µm (IEST-RP-CC004.3, Sec 6.1.4)	82.42 x 10 <sup>6</sup> counts/m <sup>2</sup>
Fiber Count > 100 microns (thousands / m <sup>2</sup> )	14.3
<b>Ions</b> (IEST-RP-CC004.3, Sec 7.2.2)	
Chloride (Cl)	0.0012 mg/g
Sulphate (SO <sub>4</sub> )	No detection
Sodium (Na)	No detection
Potassium (K)	No detection
Magnesium (Mg)	0.0500 mg/g
Calcium (Ca)	0.0660 mg/g
<b>Organics by FTIR</b> (IEST-RP-CC004.3, Sec 7.2.1)	No Silicone oil, Amide, DOP detected

#### Packaging:

ITEM	Size	Packaging
NT1-44 (Made in USA)	4" x 4"	1200 wipes/bg, 12 bgs/cs
NT1-66 (Made in USA)	6" x 6"	600 wipes/bg, 10 bgs/cs
NT1-77 (Made in USA)	7" x 7"	330 wipes/bg, 18 bgs/cs
NT1-99 (Made in USA)	9" x 9"	300 wipes/bg, 12 bgs/cs
NT10-99 (Made in China)	9" x 9"	300 wipes/bg, 12 bgs/cs
NT1-1212 (Made in USA)	12" x 12"	150 wipes/bg, 14 bgs/cs
NT10-1212 (Made in China)	12" x 12"	150 wipes/bg, 14 bgs/cs
NT1-1818 (Made in USA)	18" x 18"	150 wipes/bg, 5 bgs/cs
NT1-99CB (Sterile) (Made in USA)	9" x 9"	25 wipes/bg, 6 bgs/master bg - 10 master bgs/cs
NT1-1212CB (Sterile) (Made in USA)	12" x 12"	20 wipes/bg, 6 bgs/master bg - 7 master bgs/cs

The above is typical physical property test data applicable to the sample reference name and should not be construed as a specification.

**Disclaimer:** The information supplied in this document is for guidance only and should not be construed as a warranty. All implied warranties are expressly disclaimed, including without limitation any warranty of merchantability and fitness for use. All users of the material are responsible for assuring that it is suitable for their needs, environment and end use. All data is subject to change as High-Tech Conversions deems appropriate.